

**CERTIFICATE OF ANALYSIS**

**CERTIFICATE NO.**

**1009261.6**

**CUSTOMER**

**CUSTOMER REF.**

**MBE 172**

Microban (Europe Ltd)  
Talon House  
Presley Way  
Crownhill  
Milton Keynes  
MK8 0ES  
UK

**SAMPLE DETAILS**

**DATE RECEIVED**

**21-Apr-08**

Velteck Systems S.A.

**METHOD: (Determination of Antibacterial Activity using Test Based on JIS Z 2801: 2000)**

**DATE ANALYSED**

23-Apr-08

**DATE REPORTED**

29-May-08

**RESULTS (AS CFU CM -2)**

SAMPLE		CONTACT TIME		LOG REDUCTION	% REDUCTION
		0	24		
Polypropylene	<i>Shigella dysenteriae</i>	8.5E+03	1.6E+03		
ABS Black - Control Blank	<i>Shigella dysenteriae</i>	8.5E+03	5.9E+02		
ABS Black - 5% 2110-200	<i>Shigella dysenteriae</i>	8.5E+03	8.3E+01	2.0	99.02%

The above data shows the difference in the population following contact with the surface of the samples listed for 24 hours at 35°C under a RH of > 95% relative to the initial population.

NS = Poor survival on control supplied.

INDUSTRIAL MICROBIOLOGICAL SERVICE LTD  
PALE LANE  
HARTLEY WINTNEY  
HANTS  
RG27 8DH  
UK

PETER D ASKEW  
MANAGING DIRECTOR

